

# PU7310 SEALER

## PRODUCT DESCRIPTION

Arturo PU7310 Sealer is a very low emission, transparent, matte, waterborne, 2-component sealer based on polyurethane resin.

## AREA OF APPLICATION\*\*\*

Suitable as a very low emission, transparent, matte, durable, wear-resistant, UV-stable finish on Arturo Self-smoothing floors for light-duty usage.

Arturo PU7310 Sealer is particularly suitable as a finish for:

- ▶ Arturo PU2030 Self-smoothing Floor
- ▶ Arturo PU2050 Self-smoothing Floor
- ▶ Arturo PU2035 Self-smoothing Floor
- ▶ Arturo PU2060 Self-smoothing Floor
- ▶ Arturo EP3950 Sealer
- ▶ Arturo EP7950 Sealer
- ▶ Arturo Concreta Self-smoothing floor
- ▶ Arturo Mistral Self-smoothing floor

For application on other surfaces, request special advice.

## PRODUCT FEATURES/BENEFITS

- ▶ Matte
- ▶ High UV stability
- ▶ Easy to process
- ▶ Very durable and scratch resistant
- ▶ Good resistance to chemicals
- ▶ Solvent-free
- ▶ Waterborne
- ▶ Very easy to clean
- ▶ Very low emission
  - AgBB certified



## PRODUCT DATA

|                |                                                    |
|----------------|----------------------------------------------------|
| Packaging size | Set: A + B = 2,5 kg:<br>A = 2,12 kg<br>B = 0,38 kg |
|                | Set: A + B = 5 kg:<br>A = 4,25 kg<br>B = 0,75 kg   |
|                | Set: A + B = 10 kg:<br>A = 8,50 kg<br>B = 1,50 kg  |
| Shelf life     | Approx. 6 months from the date of production       |

## TECHNICAL DATA

|                                              |                                                        |
|----------------------------------------------|--------------------------------------------------------|
| Density                                      | Approx. 1,05 kg/dm <sup>3</sup>                        |
| Consumption                                  | Approx. 90-100 g/m <sup>2</sup> per layer              |
| Mixing ratio                                 | 85.0 weightparts comp. A<br>15.0 weightparts comp. B   |
| Pot life                                     | Approx. 50 minutes*                                    |
| Dust-dry                                     | After approx. 90 minutes*                              |
| Ready for foot traffic                       | After approx. 4 hours*                                 |
| Recoatable                                   | After approx. 4 hours, apply second layer in 24 hours* |
| Full mechanical resilience                   | After 3 days*                                          |
| Chemically resistant                         | After 7 days*                                          |
| Frost resistance                             | No                                                     |
| Solids content                               | 35%                                                    |
| Viscosity (23°C)                             | Approx. 300 mPa·s                                      |
| Abrasion resistance Taber (7d/21°C/60% r.h.) | 10 mg (CS-10/1000U/1000g)<br>20 mg (CS-17/1000U/1000g) |



Good resistance to chemicals



Impermeable



Low maintenance and maintenance friendly



No seams



Hard-wearing and good scratch resistance



UV-stable



Slip-resistant option

## SUBFLOOR PREPARATION

The floor surface or Arturo floor must be fully cured (tack-free) and suitable for foot traffic. A Arturo floor must be acclimatised at room temperature for ca. 24 hours before the sealer can be applied. For application after 24 hours we recommend, for optimal adhesion, lightly roughening the surface with a red pad or with a sanding disc (180 grit). Then remove all dust from the surface.

Prior to application on epoxy resin coatings it is necessary to first roughen the surface with a black pad or with a sanding disc (180 grit).

## PROCESSING CONDITIONS

Minimum temperature of the subfloor: + 10°C and + 3°C above the dew point. Protect from condensation.

Room/processing temperature:

- ▶ Min: + 15°C
- ▶ Max: + 25°C
- ▶ Optimum: + 20°C

Minimum relative humidity: 40%

Maximum relative humidity: 75%

These conditions must be observed while processing as well as curing.

The processing of waterborne coating/sealers systems requires suitable ventilation and temperature. Draughts must be avoided. Too high humidity and draughts can adversely affect the curing, degree of gloss and the structure of the cured material.

(In general, higher temperatures shorten the pot life, whilst lower temperatures prolong the curing)

## PROCESSING INSTRUCTIONS

Stir component A thoroughly. Add component B and immediately mix for at least 2 minutes with an electrical mixer (speed ca. 300 – 400 rpm). Then transfer the mixture to a clean container by passing the mixed material through a sieve. For processing we recommend using a bucket with wipe-off grid.

Always apply the sealers in 2 layers. Apply to the floor edges using a brush (only apply a few metres in order to avoid drying at the edges) and then immediately roll with a 10 cm wide nylon roller (14 mm pile height). Apply the material thinly and evenly with a saturated 25 cm wide nylon roller (14 mm pile height) working cross-wise to get a closed layer (90 - 110 g/m<sup>2</sup>) over the whole surface. Within 10 minutes roll the surface again using a 50 cm wide nylon roller (14 mm pile height), lightly wetted with material, in only one direction and without applying pressure. Roll cross-wise to the already applied material. For an optimal result the application and rolling should be carried out in one working step, wearing blunt spiked shoes to walk on the freshly applied sealer. For larger areas we recommend that at least 2 persons apply the sealant. Regularly change the nylon roller and after an interruption to the work always use a new roller. After 4-24 hours apply the second layer in exactly the same way as the first layer. Attention note! If the second layer PU7310 Sealer will be applied after 24 hours, make

sure the first layer is properly cleaned and roughened with a sanding disc for a optimum adhesion. The risk of these products creating unsightly roller marks and lines is inherent to these products, so we can not fully rule this out. Following our guidelines will however, leave this risk to a minimum.

### Anti-slip variants

The anti-slip variant of Arturo PU7310 must always be applied in two layers, with Ballotini 75-150 µm added to the first layer. The second layer is applied without Ballotini.

Stir component A thoroughly. Add component B and immediately mix for at least 2 minutes with an electrical mixer (speed ca. 300 – 400 rpm). Then add the supplied Ballotini 75-150 µm and mix thoroughly again with a mixer that is also able to mix the material at the bottom of the container (mixing time ca. 2 minutes). Then transfer all the mixture to a clean container. For processing we recommend using a bucket with wipe-off grid.

The Ballotini 75-150 µm can be ordered separately.

The processing procedure is the same as for applying the sealant without anti-slip particles.

After 4-24 hours apply the second layer in exactly the same way as the first layer, but without addition of anti-slip particles.

Do not keep residues in containers.

### Attention

The processing of waterborne sealer systems requires suitable ventilation and temperature. Draughts must be avoided. Too high humidity and draughts can adversely affect the curing, degree of gloss and the structure of the cured material. In general, higher temperatures and low humidity shorten the pot life, whilst lower temperatures and high prolong the curing.

### Batches

We hence recommend using products with the same batch for coating a floor. The batch number of a product is shown on the packaging.

Tips for castors on chairs (BS EN 12529)

For long-term protection of the coating, chairs should have type W castors. We also recommend using transparent polycarbonate protective mats for chairs.

Abrasive stress can lead to scratching of the coating. We hence recommend specifying clean walking zones to minimise sand and dirt ingress.

## DIBT GUTACHTEN

DIBt Gutachten Nr. G-156-19-000 for the assessment of compliance with the construction requirements with regard to health protection (ABG) according MVVTB 2019/1, attachment 8, when installing the flooring systems "Arturo PU".

## CLEANING

Use Arturo Cleaning Cloths from Uzin Utz Nederland bv for fresh contaminations.

## DATA SOURCES

All technical data, measurements, etc. given on this data sheet are based on laboratory tests. Due to circumstances beyond our control, actual data may deviate from the indicated values.

## DISCLAIMER

The information on this product sheet concerning the processing and application of this product is based on our experience with the product under standard conditions and with correct product storage and use. In practice, differences between equipment, subfloors and working conditions mean that no guarantee for a specific work result nor any liability, arising out of any legal relationship whatsoever, can be inferred either from the information on this data sheet or from any verbal advice given, unless caused by intent or gross negligence on our part. In this case the user must demonstrate that he has promptly forwarded to us in writing all necessary information for proper and effective evaluation of the circumstances. Users must test the products to check whether they are suitable for the intended application. We reserve the right to amend the information on technical data sheets. The intellectual property rights of third parties must be heeded. The most recent technical data sheet always applies. This can be requested from us or downloaded from [www.arturoflooring.com](http://www.arturoflooring.com). Our general terms and conditions of sale and delivery also apply.

## PROTECTION OF THE WORKPLACE AND ENVIRONMENT

Water-based seal with linking agent containing isocyanate, solvent content less than 5 %. Suitable as a substitute material for high solvent content materials used for parquet surface treatment. Component A: Requires no special protection or precautions in general use. Component B: contains pre-polymerised isocyanate. Harmful if inhaled. May cause an allergic skin reaction. May cause respiratory irritation. Both components: Provide good ventilation during and after use. Use barrier cream and protective gloves / goggles. Avoid contact with skin or contact with eyes. After contact with skin, wash immediately with plenty of water and soap. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. Observe safety information on product label as well as safety data sheet.

## DISPOSAL

Where possible, collect product residues and re-use. Do not empty into drains, sewers or ground. Empty, scraped and drip-free containers are recyclable. Liquid residues as well as containers with liquid residues are special waste, those with mixed and cured residues are Construction Waste. Therefore collect waste material, mix both components, allow to harden, then dispose as Construction Waste.

\* At 20°C, 65% relative humidity.

\*\* Avoid large temperature fluctuations and differences, this can lead to a temperature shock which has a negative influence on the final result.

\*\*\* For recreation rooms systems with AgBB certification must be used.