

EP1851 SKIRTING MORTAR

PRODUCT DESCRIPTION

Arturo EP1851 Skirting Mortar is a 2-component, epoxy-based mortar system with mineral fillers.

AREA OF APPLICATION***

It is especially suitable for skirting and upstands in:

- ▶ Sanitary areas
- ▶ Abattoirs
- ▶ Kitchens
- ▶ Chemical stores
- ▶ Sumps

PRODUCT FEATURES/BENEFITS

- ▶ Easy to apply
- ▶ Very smooth surface
- ▶ Closed surface
- ▶ Good resistance to chemicals
- ▶ Resistant to impacts, shock and abrasion
- ▶ Coloured

TEST/APPROVAL

- ▶ Testing of the chemical resistance in accordance with DIN EN ISO 2812-3.
- ▶ Testing on resistance to wear according to BCA.



PRODUCT DATA

Packaging size	Set: A + B = 10 kg: A = 9,70 kg B = 0,30 kg
Shelf life	Approx. 12 months from date of production.
Colour	Light grey

TECHNICAL SPECIFICATIONS

Tensile strength (7d/21°C/60% r.h.)	25 - 27 MPa** (N/mm ²)
Compressive strength (7d/21°C/60% r.h.)	58 - 62 MPa ** (N/mm ²)
Density	2.0 kg/dm ³
Consumption	Approx. 1,5 kg/m ² /6 cm height Approx. 2,0 kg/m ² /10 cm height
Mixing ratio	97.0 part by weight comp. A 3.0 part by weight comp. B
Pot life	Approx. 30 minutes*
Dust-dry	After approx. 6 hours*
Ready for foot traffic	After approx 16 hours*
Recoatable	In approx. 16 to max 24 hours*
Full mechanical resilience	After 3 days*
Chemically resistant	After 7 days*
Frost resistance	Yes**
Solids content	100%



Impermeable



No seams



Good resistance to chemicals



Hard-wearing and good scratch resistance



Universal use



Low maintenance and maintenance friendly

SUBFLOOR

The substrate must be firm, able to bear sufficient loads and have adequate grip. It must be free of grease, oil and non-adherent components. It must also be free of any layers or contaminants that could reduce the adhesion. (Compressive strength at least 25 MPa (N/mm²), average tensile strength >1.5 MPa (N/mm²), smallest single value > 1.0 MPa (N/mm²)).

Prior to work, the substrate must be adequately dry:

- ▶ Cement screed subfloors ≤ 4 CM%
- ▶ Anhydrite: ≤ 0,3 CM%.
- ▶ Magnesite: ≤ 4 CM%.
- ▶ Concrete class > B35: ≤ 3 CM%.
- ▶ Concrete class < B35: ≤ 4 CM%.

For Sweden and the UK, below 75% r.h.

SUBFLOOR PREPARATION

Remove non-adherent layers and contaminants by suitable mechanical means (e.g. shot blasting, sanding or brushing). Then remove all dust using an industrial vacuum cleaner. Larger repairs and the filling of gaps, holes and other unevenness must be carried out with Arturo EP1500 repair mortar.

Cement- and anhydrite based subfloors needs to be prepared with Arturo EP6850 Skirting Primer or an other suitable Arturo product.

PROCESSING CONDITIONS

Minimum substrate temperature: + 10°C and + 3°C above the dew point.

Room/processing temperature:

- ▶ Min: + 15°C
- ▶ Max: + 30°C
- ▶ Optimum: + 20°C

Maximum relative humidity: 80%

(In general, higher temperatures shorten the pot life, whilst lower temperatures prolong the curing).

These conditions must be observed while processing as well as curing.

PROCESSING INSTRUCTIONS

Stir component A thoroughly. Add component B and mix for at least 3 minutes with an electrical mixer (speed ca. 300 – 400 rpm). Apply the mixture to the substrate and distribute with a trowel. Then compress the surface, preferably manually with a trowel.

SHELF LIFE

The two components must be acclimatised in the working area prior to use for at least 24 hours. Store under dry, cool and frost-free conditions in the original, sealed containers.

CLEANING

Use Arturo Cleaning Cloths from Uzin Utz Nederland bv for fresh contaminations.

EU-REGULATION 2004/42

In accordance with EU Regulation 2004/42 the maximum permitted concentration of VOCs (product category IIA/j, type sb) is 500 g/l in the ready-to-use state (version 2010). The VOC content of Arturo EP1851 in the ready-to-use state is < 500 g/l.

DATA SOURCES

All technical data, measurements, etc. given on this data sheet are based on laboratory tests. Due to circumstances beyond our control, actual data may deviate from the indicated values.

DISCLAIMER

The information on this product sheet concerning the processing and application of this product is based on our experience with the product under standard conditions and with correct product storage and use. In practice, differences between equipment, subfloor and working conditions mean that no guarantee for a specific work result nor any liability, arising out of any legal relationship whatsoever, can be inferred either from the information on this data sheet or from any verbal advice given, unless caused by intent or gross negligence on our part. In this case the user must demonstrate that he has promptly forwarded to us in writing all necessary information for proper and effective evaluation of the circumstances. Users must test the products to check whether they are suitable for the intended application. We reserve the right to amend the information on technical data sheets. The intellectual property rights of third parties must be heeded. The most recent technical data sheet always applies. This can be requested from us or downloaded from www.arturoflooring.com. Our general terms and conditions of sale and delivery also apply.

PROTECTION OF THE WORKPLACE AND ENVIRONMENT

Solvent-free. Non flammable. Comp. A: Contains epoxy resin/irritant. May damage fertility. Restricted to professional users. Comp. B: Contains amine hardener/corrosive. Both components: May cause irritations or burns to eyes, skin or respiratory system. May cause sensitisation by skin contact. After contact with skin, wash immediately with plenty of water and soap. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. Use barrier cream, protective gloves and safety-goggles. In liquid form, "hazardous to the environment", therefore do not allow into drains, water courses or landfill. Observe safety information on product label as well as safety data sheet.

DISPOSAL

Where possible, collect product residues and re-use. Do not empty into drains, sewers or ground. Empty, scraped and drip-free containers are recyclable. Liquid residues as well as containers with liquid residues are special waste, those with mixed and cured residues are Construction Waste. Therefore collect waste material, mix both components, allow to harden, then dispose as Construction Waste.

* At 20°C, 65% relative humidity.

** Avoid large temperature fluctuations and differences, this can lead to a temperature shock which has a negative influence on the final result.

*** For recreation rooms systems with AgBB certification must be used.